



**Size Board**

<b>LENGTH</b>	1860 mm
<b>WIDTH</b>	148 mm
<b>TOTAL THICKNESS</b>	10 mm
<b>THICKNESS TOP LAYER</b>	2.5 mm
<b>PLANK QUANTITY</b>	Min. 10 Pl. x 1860 mm

**Size Pack**

<b>PACK LENGTH</b>	1870 mm
<b>PACK WIDTH</b>	160 mm
<b>PACK THICKNESS</b>	130 mm
<b>PACK WEIGHT</b>	20 kg
<b>LAYERS/PACK</b>	12
<b>M<sup>2</sup>/PACK</b>	3.3 m <sup>2</sup>

**Size Pallet**

<b>LENGTH PALLET</b>	1890 mm
<b>WIDTH PALLET</b>	1120 mm
<b>HEIGHT PALLET</b>	1160 mm
<b>WEIGHT PALLET</b>	1135 kg
<b>PACKS/PALLET</b>	56
<b>M<sup>2</sup>/PALLET</b>	184.8 m <sup>2</sup>

**Characteristics**


**Top layer**

<b>WOOD SPECIES</b>	Oak
<b>LATIN NAME</b>	Quercus Mongolica
<b>GRADE</b>	ABC
<b>CONSTRUCTION</b>	2-layer
<b>THICKNESS TOP LAYER</b>	2.5 mm
<b>STRIPS</b>	1 strip
<b>CUTTING METHOD</b>	Sawn veneer
<b>BEVEL</b>	Micro bevel Two long sides (0,50 mm)
<b>COLOUR FINISH</b>	Smoked White oiled
<b>SURFACE STRUCTURE</b>	Brushed

**Composition of the support**

<b>SUPPORT TYPE</b>	Multiplex support
<b>WOOD SPECIES SUPPORT</b>	Mixed Light Hardwood
<b>SUPPORT CONSTRUCTION</b>	Multiplex (6 layers)
<b>TOTAL THICKNESS SUPPORT</b>	7.5 mm
<b>ADHESION</b>	Crosswise (Casco)

**Installation**

<b>SYSTEM</b>	<b>APPLICATIONS</b>	<b>UNDERFLOOR HEATING</b>
Tongue and groove system	Light household use	Yes
	Moderate commercial use	<b>RESANDABLE</b>
	Normal commercial use	Resandable
	Normal household use	
	Intensive commercial use	

**Certification**

This product conforms to CE standard EN 14342:2005 + A1: 2008 - Level 4 for flooring type BS EN 13489:2002 (Wood and parquet flooring, Multilayer parquet)

- Formaldehyde emission, determined according to standard EN 13183-1: E1
- Moisture content, determined according to standard EN 13183-1: 10% (+ / -2%). Fits in dry areas with a moisture content of 50% to 60%
- Width Shrinkage, complies with standard EN 13647
- Reaction to fire, determined according to standard EN 13501-1: Dfl-S1
- Does not contain any PCP (pentachlorophenol)

**Technical specifications**

- Hardness: N / mm<sup>2</sup> (Birrell Hardness) 3.40
- Thermal conductivity:  $\lambda$  14, 00 (W / (mk)) R = 0.11 m<sup>2</sup> K / W

Additional tests:

- Tested for delamination and stability according to standard EN1910 (cf. 15-189-BRUT CLASSIC)
- The bonding was tested according to EN311 standard (see 15-189-BRUT CLASSIC)